

EUROFINS Umwelt Ost GmbH · Niederlassung Freiberg  
Lindenstraße 11 D-09627 Bobritzsch-Hilbersdorf

**AENOR INTERNACIONAL, S.A.U.**  
**CL Genova 6**  
**28004 Madrid**  
**SPANIEN**

Title: **Test report to order 11713404**  
Test report: **No. 1008328094**


Project: **No. 1008328**  
Title of project: **AENOR REFERENCE 0142003, COMPANY HIJOS DE TOMAS MARTÍN**  
Number of samples: **1 sample**  
Sample type: **wood pellets**  
Sampler: **client**  
Receipt of samples: **2017-06-06**  
Test period: **2017-06-06 - 2017-06-14**

The test results refer solely to the analysed test specimen. Unless the sampling was done by our laboratory or in our sub-order the responsibility for the correctness of the sampling is disclaimed. This test report is only valid with signature and may only be further published completely and unchanged. Extracts or changes require the authorisation of the EUROFINS UMWELT in each individual case.

Our General Terms & Conditions of Sale (GTCS) are applicable, as far as no specific agreements do exist.  
The GTCS are available on <http://www.eurofins.de/umwelt/avb.aspx>.

Accredited test laboratory according to DIN EN ISO/IEC 17025 notification under the DAkkS German Accreditation System for Testing. The accreditation shall apply for the tests listed in the certificate.

Freiberg, 2017-06-14

  
Dipl.-Chem. A. Ulbricht  
Head of Laboratory



Deutsche  
Akkreditierungsstelle  
D-PL-14081-01-00

**Niederlassung Freiberg**  
Lindenstraße 11  
D-09627 Bobritzsch-Hilbersdorf  
Tel. +49 (0) 3731 2076 500  
Fax +49 (0) 3731 2076 555  
[info\\_freiberg@eurofins.de](mailto:info_freiberg@eurofins.de)

**Hauptsitz:**  
Löbstedter Straße 78  
D-07749 Jena  
[info\\_jena@eurofins.de](mailto:info_jena@eurofins.de)  
[www.eurofins-umwelt-ost.de](http://www.eurofins-umwelt-ost.de)

**Geschäftsführer:**  
Dr. Heinrich Ruholl, Dr. Benno Schneider,  
Axel Ulbricht  
Amtsgericht Jena HRB 202596  
USt.-ID.Nr.: DE 151 28 1997

**Bankverbindung: NORD LB**  
BLZ 250 500 00  
Kto 150 334 779  
IBAN DE91 250 500 00 0150 334 779  
BIC/SWIFT NOLA DE 2HXXX

# Test report to order 11713404

No. 1008328093 page 2 / 3

Project: AENOR REFERENCE 0142003, COMPANY HIJOS DE TOMAS MARTÍN

Analysis according to EN plus edition august 2015

Parameter	Unit	LOQ	limits			Sample designation	HIJOS DE TOMAS MARTÍN
			EN Plus-A1	EN Plus-A2	EN Plus-B	Lab-ID#	117049452
						Method	

## Quality characteristics

diameter, D	mm ar		6±1 or 8±1	6±1 or 8±1	6±1 or 8±1	DIN EN ISO 17829 (FR-JE02)	6,1
length, L	mm ar		3,15 ≤ L ≤ 40	3,15 ≤ L ≤ 40	3,15 ≤ L ≤ 40	DIN EN ISO 17829 (FR-JE02)	according
water content, M	% w/w ar	0,1	≤ 10	≤ 10	≤ 10	DIN EN ISO 18134-2 (FR-JE02)	4,9
ash content, A (550°C)	% w/w db	0,1	≤ 0,7	≤ 1,2	≤ 2,0	DIN EN ISO 18122 (FR-JE02)	0,44
mechanical durability, DU	% w/w ar		≥ 98,0	≥ 97,5	≥ 97,5	DIN EN ISO 17831-1 (FR-JE02)	98,9
fine portion, F (< 3,15 mm)	% w/w ar	0,1	≤ 1,0 <sup>1</sup> or ≤ 0,5 <sup>2</sup>	≤ 1,0 <sup>1</sup> or ≤ 0,5 <sup>2</sup>	≤ 1,0 <sup>1</sup> or ≤ 0,5 <sup>2</sup>	DIN EN ISO 18846 (FR-JE02)	< 0,1
bulk density, BD	kg/m <sup>3</sup> ar		600 ≤ BD ≤ 750	600 ≤ BD ≤ 750	600 ≤ BD ≤ 750	DIN EN ISO 17828 (FR-JE02)	660
net calorific value, Q (H u,p)	kWh/kg ar	0,06	≥ 4,6	≥ 4,6	≥ 4,6	DIN EN ISO 18125 (FR-JE02)	5,04
nitrogen total, N	% w/w db	0,05	≤ 0,3	≤ 0,5	≤ 1,0	DIN EN ISO 16948 (FR-JE02)	< 0,05
sulfur total, S	% w/w db	0,005	≤ 0,04	≤ 0,05	≤ 0,05	DIN EN ISO 16994 (FR-JE02)	0,007
chlorine total, Cl	% w/w db	0,005	≤ 0,02	≤ 0,02	≤ 0,03	DIN EN ISO 16994 (FR-JE02)	0,008

## Determination of minor elements

arsenic, As	mg/kg db	0,8	≤ 1	≤ 1	≤ 1	DIN EN ISO 16968 (FR-JE02)	< 0,8
lead, Pb	mg/kg db	2	≤ 10	≤ 10	≤ 10	DIN EN ISO 16968 (FR-JE02)	< 2
cadmium, Cd	mg/kg db	0,2	≤ 0,5	≤ 0,5	≤ 0,5	DIN EN ISO 16968 (FR-JE02)	< 0,2
chromium total, Cr	mg/kg db	1	≤ 10	≤ 10	≤ 10	DIN EN ISO 16968 (FR-JE02)	1
copper, Cu	mg/kg db	1	≤ 10	≤ 10	≤ 10	DIN EN ISO 16968 (FR-JE02)	1
nickel, Ni	mg/kg db	1	≤ 10	≤ 10	≤ 10	DIN EN ISO 16968 (FR-JE02)	< 1
mercury, Hg	mg/kg db	0,07	≤ 0,1	≤ 0,1	≤ 0,1	DIN EN ISO 16968 (FR-JE02)	< 0,05
zinc, Zn	mg/kg db	1	≤ 100	≤ 100	≤ 100	DIN EN ISO 16968 (FR-JE02)	11

# Test report to order 11713404

No. 1008328093 page 3 / 3

Project: AENOR REFERENCE 0142003, COMPANY HIJOS DE TOMAS MARTÍN

Analysis according to EN plus edition august 2015						Sample designation	HIJOS DE TOMAS MARTÍN
Parameter	Unit	LOQ	limits			Lab-ID#	117049452
			EN Plus-A1	EN Plus-A2	EN Plus-B	Method	

## Ash melting behaviour (oxidizing atmosphere) on ash 815°C

shrinkage start temperature, SST	°C		can be given	can be given	can be given	DIN CEN/TS 15370-1 (FR-JE02)	1020
deformation temperature, DT	°C		≥ 1200	≥ 1100	≥ 1100	DIN CEN/TS 15370-1 (FR-JE02)	1300
hemisphere temperature, HT	°C		can be given	can be given	can be given	DIN CEN/TS 15370-1 (FR-JE02)	1330
flow temperature, FT	°C		can be given	can be given	can be given	DIN CEN/TS 15370-1 (FR-JE02)	1350

comment:

additive: (limits: ≤ 1,8 % w/w during production + 0,2 % w/w after production - sort and amount must be specified)

Information given by the customer: no information.

length: up to 1 % of pellets can be longer than 40mm. Maximum length for pellets is 45mm.

fine portion: 1) at the end of production or by loading vehicles for delivery to the customer  
2) for filling in pellet bags or big bags

mechanical durability: by loading for transport (vehicle, ship) after production

Hu,p: net calorific value at constant pressure

ar: as received

db: dry basis

--

EUROFINS UMWELT is not liable for accuracy of the cited limits.

## Explanations on Locations and Accreditations

The parameters identified by FR have been performed by the laboratory EUROFINS Umwelt Ost GmbH (Bobritzsch-Hilbersdorf). The accreditation code JE02 identifies the parameters accredited according to DIN EN ISO/IEC 17025:2005 D-PL-14081-01-00.