

Eurofins Umwelt Ost GmbH - Lindenstraße 11 - Gewerbegebiet Freiberg Ost -
D-09627 Bobritzsch-Hilbersdorf

AENOR CONFIA, S.A.U.
Calle Genova, Num
28004 Madrid
SPAIN

Title : **Extract from (Batch): AR-24-FR-057532-01 (12444368)**

Test report number : **EX-24-FR-002959-01**

Project name : **HIJOS DE TOMÁS MARTÍN, S.L. 2018/0967/ENP/02**

Number of samples : **2**

Sample type: **wood pellets**

Sample Taker: **not specified, sample(s) were delivered to lab**

Sample reception date : **2024-10-10**

Sample processing time : **2024-10-10 - 2024-10-21**

Comment: **CENTRO DE DOÑA SANTOS**

The test results solely refer to the analysed test specimen. Unless the sampling was done by our laboratory or in our sub-order the responsibility for the correctness of the sampling is disclaimed. This analytical report is electronically signed and may only be further published completely and unchanged. Extracts or changes require the authorisation of the EUROFINS UMWELT in each individual case.

Our General Terms & Conditions of Sale (GTCS) are applicable, as far as no specific agreements do exist. The GTCS are available on <http://www.eurofins.de/umwelt/avb.aspx>.

Accredited test laboratory according to DIN EN ISO/IEC 17025:2018 DAkkS notification under the DAkkS German Accreditation System for Testing. The laboratory is according (D-PL-14081-01-00) accredited.

Ulrich Erler
Analytical Service Manager

+49 3731 2076 510

Digitally signed 10/23/2024

Stefan Seifert

Analytical Service Manager



Parameter	Lab	Accr.	Method	Limit values		Description		0171798		0171829	
				DIN Plus anl.	DIN Plus wf.	Sample number		124159690		124159691	
				LOQ	Unit	ar	db	ar	db		
Quality characteristics											
Length	FR	F5	DIN EN ISO 17829: 2016-03	4)				o.k.	-	-	-
Diameter	FR	F5	DIN EN ISO 17829: 2016-03	5)			mm	6.0	-	-	-
Moisture	FR	F5	DIN EN ISO 18134-2: 2017-05	10		0.1	% (w/w)	5.0	-	-	-
Ash content (550°C)	FR	F5	DIN EN ISO 18122: 2016-03		0.6	0.1	% (w/w)	0.4	0.4	-	-
Durability	FR	F5	DIN EN ISO 17831-1: 2016-05	≥ 98			% (w/w)	99.2	-	-	-
Bulk density	FR	F5	DIN EN ISO 17828: 2016-05	600 - 750			kg/m ³	687	-	-	-
Particle density	FR	F5	DIN EN ISO 18847: 2016-12				g/cm ³	1.25	-	-	-
Gross calorific value (qV,gr)	FR	F5	DIN EN ISO 18125: 2017-08			200	kJ/kg	19900 ¹⁾	20900 ¹⁾	-	-
Net calorific value (qp,net)	FR	F5	berechnet nach DIN EN ISO 18125: 2017-08	≥ 4.6		0.06	kWh/kg	5.15 ²⁾	5.46 ²⁾	-	-
Carbon	FR	F5	DIN EN ISO 16948: 2015-09			0.2	% (w/w)	48.9	51.5	-	-
Nitrogen	FR	F5	DIN EN ISO 16948: 2015-09		0.3	0.05	% (w/w)	0.10	0.11	-	-
Hydrogen	FR	F5	DIN EN ISO 16948: 2015-09			0.1	% (w/w)	5.6	5.9	-	-
Oxygen	FR	F5	DIN EN ISO 16993: 2016-11				% (w/w)	39.9	42.0	-	-
Sulphur	FR	F5	DIN EN ISO 16994: 2016-12		0.04	0.005	% (w/w)	0.007	0.008	-	-
Chlorine	FR	F5	DIN EN ISO 16994: 2016-12		0.02	0.005	% (w/w)	< 0.005	< 0.005	-	-
Fine portion < 3,15 mm	FR	F5	DIN EN ISO 5370: 2022-03 E	0.5 ⁷⁾		0.1	% (w/w)	-	-	0.2	-
Coarse pellet fines, CPF > 3,15 - < 5,6 mm	FR	F5	DIN EN ISO 5370: 2022-03 E			0.1	% (w/w)	-	-	0.4	-

Parameter	Lab	Accr.	Method	Limit values		Description		0171798		0171829	
				DIN Plus anl.	DIN Plus wf.	Sample number		124159690		124159691	
						LOQ	Unit	ar	db	ar	db

Trace elements acc. to DIN EN ISO 16968: 2015-09

Arsenic (As)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		1	0.8	mg/kg	-	< 0.8	-	-
Lead (Pb)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		10	2	mg/kg	-	< 2	-	-
Cadmium (Cd)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		0.5	0.2	mg/kg	-	< 0.2	-	-
Chromium (Cr)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		10	1	mg/kg	-	< 1	-	-
Copper (Cu)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		10	1	mg/kg	-	< 1	-	-
Nickel (Ni)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		10	1	mg/kg	-	< 1	-	-
Mercury (Hg)	FR	F5	DIN EN ISO 12846 (E12): 2012-08		0.1	0.05	mg/kg	-	< 0.05	-	-
Zinc (Zn)	FR	F5	DIN EN ISO 17294-2 (E29): 2017-01		100	1	mg/kg	-	7	-	-

Ash melting behaviour (ox. atmo.) 815°C

Shrinkage start temp SST	FR	F5	DIN EN ISO 21404: 2020-06		6)		°C	-	1050	-	-
Deformation temp DT	FR	F5	DIN EN ISO 21404: 2020-06		≥ 1200		°C	-	1440	-	-
Hemisphere temp HT	FR	F5	DIN EN ISO 21404: 2020-06		6)		°C	-	1480 ³⁾	-	-
Flow temp FT	FR	F5	DIN EN ISO 21404: 2020-06		6)		°C	-	1490	-	-

Explanations

LOQ - Limit of quantification

ar - as received

db - dry basis

Lab - Abbreviation of the performing laboratory

Accr. - Abbreviation of the accreditation of the performing laboratory

Comments for results

¹⁾ (qV, gr) gross calorific value at constant volume

²⁾ (qp, net) net calorific value at constant pressure

³⁾ * _no definite hemisphere (hill-like form)

The parameters identified by FR have been performed by the laboratory Eurofins Umwelt Ost GmbH (Lindenstraße 11, Gewerbegebiet Freiberg Ost, Bobritzsch-Hilbersdorf). The accreditation code F5 identifies the parameters accredited according to DIN EN ISO/IEC 17025:2018 DAkkS D-PL-14081-01-00 .

Explanations regarding Limits

Analysis performed according to DINplus (wood pellets) - edition November 2021, table 1.

- 4) 3,15 - 40 mm. Amount of pellets longer than 40 mm may be up to 1 % in mass. Maximum length 45 mm.
Amount of pellets shorter than 10 mm, % in mass recommended to be stated.
- 5) D06 or D08 pellets +/- 1mm
- 6) It is recommended to state all characteristic temperatures (shrinkage starting temperature (SST), deformation temperature (DT), hemisphere temperature (HT) and flow temperature (FT)) in oxidizing conditions. Pre-ashing temperature shall be 815 °C.
- 7) In small bags (up to 20 kg) < 0,5; Bulk transport (at the time of loading) and in big bags (at time of packing) < 1,0.

The presentation of comparative values in the analytical report is a service provided by EUROFINS UMWELT. The cited comparative values (limit, guideline or other allocation values) are partially simplified and do not take into account all comments, ancillary provisions and/or exemptions of the corresponding regulations.